



TECHNICAL SPECIFICATIONS, DIMENSIONS

PRODUCT NAME	CODE
Fastfoot®	FF37, FF50, FF62, FF74
Fastbag®	FB18, FB24, FB30, FB36

SECTION I – TECHNICAL SPECIFICATIONS				
		<i>Imperial</i>	<i>Metric</i>	<i>Test Method</i>
Color	Natural			
		in	mm	
Core diameter	Cardboard	1.5	38	
Tape denier	HDPE	1000D	1000D	
		tapes/in	tapes/cm	
Construction	warp	10	3.94	
Construction	weft	10	3.94	
		.001 in	mm	
Coating	LDPE	1.2	47.2	
		oz/yd ²	g/m ²	
Weight		3.2	109	
		lbs	N	
Tensile grab	warp	171.67	763.2	ASTM D1682-64
Tensile grab	weft	155.53	691.5	ASTM D1682-64
		lbs	N	
Nominal tear	warp	35.0	156	ASTM 2262
Nominal tear	weft	35.4	157	ASTM 2262
		psi	kPa	
Mullen burst		195	1346	ASTM D3786-01
		lbs	N	
Puncture resistance				ASTM D1709-04
		grains/hr.ft ²	g/hr.m ²	
Water vapor transmission		0.0434	0.0302	ASTM E96B
		grain/hr.ft ² .in Hg	g/Pa.s.m ²	
Permeance		0.0628 perms	3.59E-09	ASTM E96B

SECTION II - DIMENSIONS				
	FF37	FF50	FF62	FF74
Imperial	Edging	Narrow	Standard	Wide
<i>Width (in)</i>	37	50	62	74
<i>Length (ft)</i>	120	120	120	120
<i>Weight (oz/yd²)</i>	3.2	3.2	3.2	3.2
<i>Weight/roll (lbs)</i>	7.8	10.5	13.0	15.5
<i>Rolls/box</i>	8	4	4	4
<i>Weight/box (lbs)</i>	63.9	43.5	53.5	63.5
<i>Box height (in)</i>	39	27	33	39
<i>Box length, width (in)</i>	10	10	10	10
Metric	Edging	Narrow	Standard	Wide
<i>Width (mm)</i>	940	1270	1575	1880
<i>Length (m)</i>	36.6	36.6	36.6	36.6
<i>Weight (gm/m²)</i>	109	109	109	109
<i>Weight/roll (kg)</i>	3.5	4.8	5.9	7.0
<i>Rolls/box</i>	8	4	4	4
<i>Weight/box (kg)</i>	29.0	19.8	24.3	28.9
<i>Box height (mm)</i>	991	686	838	991
<i>Box length, width (mm)</i>	254	254	254	254